

Molylube® Ultra Open Gear Lubricant

PRODUCT DESCRIPTION

Bel-Ray® Molylube® Ultra Open Gear Lubricant (OGL) is formulated with a high viscosity paraffinic base oil, polymers, molybdenum disulfide or moly, and graphite lubricating solids, Extreme Pressure additives and corrosion inhibitors. Molylube Ultra OGL is designed for use as an open gear priming lubricant, a running in lubricant and a service lubricant. Molylube Ultra OGL is well suited for open gear use in severe mining and industrial applications. Molylube Ultra OGL meet or exceed the typical characteristics of Caterpillar branded and other compound open gear lubricants (OGLs). All grades exceed the requirements of the Komatsu P&H 464 and Bucyrus SD4713 specification for open gear lubricants.

Molylube Ultra Open Gear Lubricant is a full-service open gear lubricant in a single product, from priming through operational lubrication. Molylube Ultra OGL provides exceptional film formation capabilities ensuring that components are fully lubricated in the hydrodynamic or full fluid film mode. This lubricant meets or exceeds open gear lubricant requirements of all major dragline, electric rope shovel and hydraulic excavator manufacturers. The special 'High Dust' version provides superior dust absorbing capabilities to reduce lubricant thickening and improve film mobility. This unique characteristic improves wear control and extends lubricant application intervals in high dust and particulate operating environments. Molylube Ultra OGL is not recommended for use in anti-friction bearings.

PRODUCT FEATURES

- High base oil viscosity
- Outstanding Extreme Pressure and anti-wear properties
- Priming, running-in and operational capabilities
- High Dust formulation features special synthetic base oils that increase fluidity

BENEFITS

- Provides a thicker lubricating film for maximum component separation and protection
- Maximizes component useful life helping to reduce replacement part costs and lost production time
- Provides excellent protection for new and used surfaces; slowly smooths rough surfaces improving contact profile and reducing contact pressure
- High Dust formulation better resists lubricant thickening and sloughing in environments with severe ambient dust levels

APPLICATIONS

- All applications requiring an ISO 18792 or AGMA 6014 Compound Open Gear Lubricant
- Priming new open gears, rollers and rails, dippers stick and handles and other sliding surfaces
- Running in rough open gears
- Operational/service lubrication of open gears, rollers & rails, bushings, dipper stick & handles, and other sliding surfaces

DISTRIBUTED BY:

Calumet Branded Products, LLC
1060 N Capitol Ave
Suite 6-401
Indianapolis, IN 46204
Technical Services: 317-328-5660
www.belray.com

To the best of our knowledge, the information contained herein is accurate, but is given without warranty or guarantee. We assume no liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for the use contemplated, the name in use and whether there is any infringement of patents is the sole responsibility of the user.

All trademarks are owned by one or more affiliates within the Calumet, Inc. organization, unless otherwise specified.

© 2026 Calumet, Inc.

6/12/2026

TECHNICAL DATA SHEET



PRODUCT DATA

Typical Properties				
Property	Test Method	Medium Light	Medium	High Dust
Base Fluid Viscosity @ 40°C (cSt)	ASTM D445	50,000	50,000	50,000
Base Fluid Viscosity @ 100°C (cSt)	ASTM D445	716	716	716
Viscosity Index	ASTM D2270	135	135	135
Apparent Viscosity @ 25°C, (cP)	ASTM D2196	2,500	10,000	20,000
Copper Corrosion, 3 h @ 100°C (Rating)	ASTM D4048	1a	1a	1a
Corrosion Preventive Properties	ASTM D1743	Pass	Pass	Pass
4-Ball EP Test, Weld Load (kgf) (Pre-dilution)	ASTM D2596	> 800 / > 1,000	> 800 / > 1,000	> 800 / > 1,000
4-Ball EP Test, Load-Wear Index (kgf) (Pre-dilution)	ASTM D2596	160	160	160
Timken Retention Test, Film Life @ 43 lbs, minutes (Pre-dilution)	US Steel Film Life	> 30	> 30	> 30
Pumpability, Lincoln Ventmeter, from 1800 psi to 600 psi, maximum		-20°C < 30 sec.	-10°C < 30 sec.	-12°C < 30 sec.
Flash Point w/ solvent, °C (°F)	ASTM D92	110 (230)	110 (230)	110 (230)
Flash Point w/o solvent, °C (°F)	ASTM D92	220 (428)	220 (428)	220 (428)
Useful Temperature Range, °C (°F)		-20 to 50 (-4 to 122)	-10 to 50 (14 to 122)	-12 to 50 (10 to 122)
Color		Black	Black	Black

HEALTH and SAFETY

Health and safety recommendations for products can be found on the Safety Data Sheet (SDS) at www.belray.com

DISTRIBUTED BY:

Calumet Branded Products, LLC
1060 N Capitol Ave
Suite 6-401
Indianapolis, IN 46204
Technical Services: 317-328-5660
www.belray.com

To the best of our knowledge, the information contained herein is accurate, but is given without warranty or guarantee. We assume no liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for the use contemplated, the name in use and whether there is any infringement of patents is the sole responsibility of the user.

All trademarks are owned by one or more affiliates within the Calumet, Inc. organization, unless otherwise specified.

© 2026 Calumet, Inc.

6/12/2026